

BODY 241 NITROSOFT 1K FINE NITRO FILLER

Technical Data Sheet No 516



VOC compliant with the regulations

One component alkyd resin modified nitrocellulose based putty

Suitable for filling and refinishing small imperfections in metallic and wooden surfaces

It can be applied over polyester knife putties, nitrocellulose or acrylic primers, and then painted over, with no 'cloud' problems

It is applied in 3-4 coats in an hour

Easy to sand either dry or with water

General Technical Description



Apply with the spatula



Non force dry
30-60 min / 20°C



IR drying 5-8 min
distance: 60 - 70cm

Surface

Suitable for filling and refinishing small imperfections in metallic and wooden surfaces

Over polyester knife putties, nitrocellulose or acrylic primers as well

Pretreatment / Cleaning of substrate



Clean substrate using a soft cloth and BODY 770 ANTISIL NORMAL / BODY 771 ANTISIL FAST.

Make sure the surface is air dried rather than wiped dry



Make sure you always use appropriate face protection and good ventilation

Product Application: Apply with a spatula when mixed with hardener directly on metallic or wooden surfaces



Apply with the spatula



P 600 – P 1000
Easily sanded with water

Flash Point:
31°C/ 88°F

Remarks:

- Do not apply over bare metal
- Do not apply at temperatures below +5°C
- It can be used by countries that do not adopt the VOC legislation as well.



5-10min / 20°C



Store in a cool place

Specific Gravity:
1.34g/cm³

Solid Content (No thinner):
62% Weight

Storage shelf life:

- Store in a cool place (+5°C - +25°C) and use within 12 months for best results. Guaranteed shelf life of 18 months in unused original containers.



Non force dry
30-60min / 20°C



Always wear protective equipment

VOC (2004/42/EC)

This product is a special refinish product based on its ingredients and its properties. The maximum VOC content in this category is 540 g/L. The VOC content in the ready for use form of this product is 400 g/L.
2004/42/IIB(b)(540)400

Theoretical Coverage:

-

Cleaning of equipment:

Clean after final use with Body 767 EXTRA NITRO THINNER



Short wave 5 – 8 min
Lamp distance: < 70cm



Follow the application instructions mentioned in this TDS



P 240 – P 400
Gives a smooth, non porous surface

For professional use only. The information displayed on this sheet has been carefully selected through a series of laboratory investigations. It is based on our best knowledge at the time of issue. The data is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check for newer updates or further information if needed for his intended purpose. The intellectual property of this product, trademarks and copyrights is protected. All rights reserved. The relevant Material Safety Data Sheet and warnings displayed on the label must be read carefully. We may modify and / or discontinue operation of all or portions of this information at any time in our sole discretion, without any notice and assume no responsibility to update the information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.